

SnappyBling Iron-on Instructions

Celebrate the Sparkle!

1. Pre-wash & test your fabric. Do not use fabric softener. Cotton & Cotton/poly, denim, canvas fabrics work best.
2. Pre-heat your iron to WOOL Setting – No Steam (Empty the water out of your iron).
3. Place your shirt on top of a hard flat surface, such as a clean wood cutting board.
4. Place a piece of Teflon sheeting or other non-sticky pressing cloth inside your shirt, under the design.
5. Remove the white backing paper from the design.
6. Place the design in the desired position, sticky side of backing down on the shirt or garment.
7. Place a pressing cloth, Teflon sheeting over the design.
8. Place your iron on top of the pressing cloth and design. Press and hold for 30-45 seconds. Apply medium pressure. Some fabrics require an additional 15-30 seconds.
9. If your design is larger than your iron move the pressing cloth with the iron and do one section at a time. Do not worry about overlap. **Hint:** Remember most irons have “Steam” holes. This area of the iron will not apply pressure to the rhinestud/stones. Move the iron as necessary.
10. Let the plastic & design cool for 2-3 minutes. (Caution: HOT SURFACE). Once cool, peel away the plastic. If there are any rhinestones sticking to the backing re-iron for another 30-40 seconds. Then repeat 8 & 9.
11. Turn the garment inside out and apply heat to the back of the design area for approximately 30 seconds.
12. Once the design is cool test by rubbing your fingers over the rhinestones/studs. If something is loose, re-iron.

Hints: Designs adhere best when using a hard, flat surface. Designs can be cut apart to create unique motifs. Trim the design with the backing paper on. Consider adding a motif to a cuff, leg, sleeve or back of a shirt. Be Creative!

Care Instructions: Turn garment inside out before washing. Use gentle cycle. We suggest line drying.

Warning: This is not a toy and is not intended for small children.
SMALL PARTS ARE CHOKING HAZARDS FOR CHILDREN.

Heat Press Instruction: Use Teflon sheets inside and on top of the design. Set at 170°C or 348°F press with medium pressure for 20-25 seconds.
COLD PEEL.